

**M**  
**MH COAT**



FS 664958



# **FINISH COAT**

# **339**

Net Weight  
Approx.  
**40KG**

## **SURFACE PREPARATION**

Ensure the applied substrate is even and remove all dust, oil, grease and etc. Any free surface water must be removed before application.

## **MIXING RATIO**

Add a 40kg of FINISH COAT 339 to 12-13 litres of water in a suitable mixing vessel. Use a mechanical hand held mixer to mix the mixture for approximately 3 to 5 minutes until the desired consistency is achieved. Ensure thorough mixing of the FINISH COAT 339, which must be cohesive and free from lump prior to use.

## **APPLICATION**

It should be applied onto the substrates using steel trowel. FINISH COAT 339 can be applied up to the thickness of 0.5mm to 1mm. It can be finished with soft hair brush or trowelled smooth. For thicker applications with several layers, the layer underneath must be "touch-dry" before applying the subsequent layer. It is important to protect the product during placement and whilst curing from direct sunlight and winds. This is to prevent rapid dehydration.

## **POT LIFE**

Approximately one hour after mixing.

## **HANDLING**

FINISH COAT 339 is non-hazardous. In case of eye contact, wash with plenty of water. If Irritation persists, seek immediate medical attention.

## **DISCLAIMER**

The use of this product is beyond the manufacturer's control and liability is restricted to the replacement of material proven faulty. The manufacturer is not responsible for any loss or damage arising from incorrect usage. Specifications are subjected to change without prior notice.